


LB/DON/111/05
03

EFFECT OF SOFTENERS ON COLOUR FASTNESS OF REACTIVE DYES

D S FERNANDO



A dissertation submitted to the Department of
Textile & Clothing Technology of the University of
Moratuwa in partial fulfillment of the
requirements for the degree of



University of Moratuwa, Sri Lanka
Electronic Theses & Dissertations
www.lib.mrt.ac.lk

MASTER OF SCIENCE IN TEXTILE STUDIES

677⁰⁵
677(043)

DEPARTMENT OF TEXTILE & CLOTHING TECHNOLOGY
UNIVERSITY OF MORATUWA
SRI LANKA

SEPTEMBER 2005

Thesis

University of Moratuwa

84170



84170

84170

DECLARATION

The work presented in the dissertation in part or whole, has not been submitted for any other academic qualification at any institution.



.....
D S Fernando
(Candidate)



.....
Mr. V A Nandasena
(Supervisor)



University of Moratuwa, Sri Lanka
Electronic Theses & Dissertations
www.lib.mrt.ac.lk

ABSTRACT

This research project is primarily aimed to study the influence of softeners on colour fastness and shade variation of cotton fabric dyed with bi-functional reactive dyes. The commercial dyes selected for the study contained, both the fluoro triazine and vinyl sulphone reactive groups, in the same molecule. Four different shades of the CIBACRON FN reactive series were applied on 100% cotton knitted fabric by exhaustion method. Each fabric piece dyed was subsequently subject to the treatment by a softener. This was followed by the assessment of colour fastness ratings for washing, light and Rubbing. Light fastness was assessed subjectively with the blue wool standard and is further confirmed objectively with the help of the spectrophotometer. The fastness ratings were compared with the softner-free samples of the same shade.

This study has revealed that the treatment with softeners has resulted in a general improvement in wash and light fastness properties Polyethylene emulsion has adversely affected washfastness irrespective of the shade. A significant reduction in the light fastness was evident when treated with cationic softeners. The dye, CIBACRON BRILLIANT BLUE FN-G has shown peculiar reduction in light fastness following treatment with all types of softeners. In addition to the above, certain other trends and patterns have also been noticed when analyzing the data collected.

TABLE OF CONTENTS

	Page
1. Introduction	1
2. Literature Review	3
2.1 Dyeing with Reactive Dyes	3
2.2 Reactive Systems	6
2.2.1 Mono functional Systems	7
2.2.2 Bifunctional Systems	10
2.3 Reactive Dye-fibre Bond	13
2.4 Fastness properties and reactive dyes	17
2.5 Light fastness of reactive azo dyes	18
2.6 Softening of Textiles	20
2.7 Instrumental Colour Assessment	27
3. Methodology	29
3.1 Materials	29
3.2 Method	29
4. Results Data & Observations	32
5. Analysis & Discussion of Results	37
6. Conclusions & Recommendations	41
7. References	54



LIST OF FIGURES, TABLES AND ANNEXES

Figures	Page
2.1 Rate of reactivity of triazines	4
2.2 Nucleophilic addition to vinyl sulphone	7
2.3 Amino fluoro-s-triazine dye	9
2.4 CI Reactive Black 5	10
2.5 CI Reactive Red 194	12
2.6 Reaction of cellulose with dichlorotriazine	13
2.7 Reaction of cellulose with aminoclorotriazine	14
2.8 Dye fibre bond formation by nucleophilic addition mechanism	14
2.9 Silicone emulsions	26
2.10 Structural formulas of amino/amido silicones	27

Tables	Page
4.1 Change in colour of the specimen	32
4.2 Staining of the adjacent fabric	33
4.3 Light fastness ratings & shade differences	34
4.4 ΔL , Δa , Δb , ΔC & ΔH values of samples	35
4.5 Rub fastness ratings (Dry & wet)	36

Annexes	Page
1 Reactive systems	42
2 Fixation of bireactive dyes on cellulose	44
3 Properties and application of softeners used	47
4 Light Fastness Assessment	52



ACKNOWLEDGEMENT

At the outset I am very grateful to Mr. V A Nandasena, Chairman/Managing Director, Vantex (Pvt) Ltd., Dehiwela and Visiting Lecturer of the Department of Textile and Clothing Technology, University of Moratuwa, who is also the Project Supervisor, for the invaluable guidance and the encouragement given to me with extreme patience and understanding.

I also wish to express my gratitude to Mr. K. Amaratunga and Ms. S. Dassanayake of Textile Training and Services Centre (TTSC) for their valuable assistance given in the preparation and analysis of samples, subject for the test.

I also offer my most grateful thanks to Mr. A. Tennakoon of A Bours & Company Ltd. for providing me the chemicals required for the study.



University of Moratuwa, Sri Lanka
Electronic Theses & Dissertations
www.lib.mrt.ac.lk

Last but not least to Ms. P. Pamaratna at Sri Lanka Standards Institution for type setting the manuscript very efficiently.

Finally I wish to extend my appreciation to my colleagues and close associates who guided and assisted me in numerous ways.